

GRPE **022** 05-03-03

**GRPE CGH<sub>2</sub> Experts**

(A sub-group of the GRPE Informal Group “Hydrogen/Fuel Cell Vehicles”)

**Agreed Changes To Annex 8  
Following The Meeting In Munich On 05 March 2003**

## **Annex 8**

### **REQUIREMENTS AND APPROVAL TEST PROCEDURES FOR SPECIFIC COMPONENTS OTHER THAN CONTAINERS**

<b>Contents</b>	<b>Page</b>
Part A	<b>PROVISIONS REGARDING THE APPROVAL OF SPECIFIC COMPONENTS OTHER THAN CONTAINERS</b>
A1	References
A2	General Requirements
A3	Approval Requirements
Part B	<b>APPROVAL TEST PROCEDURES FOR SPECIFIC COMPONENTS OTHER THAN CONTAINERS</b>
B1	Hydrogen Compatibility Test
B2	Ageing Test
B3	Corrosion Resistance Test
B4	Hydraulic Pressure Cycle Test
B5	Endurance Test
B6	Internal Leakage Test
B7	External Leakage Test
B8	Hydrostatic Pressure Test

## **Annex 8: Part A**

### **PROVISIONS REGARDING THE APPROVAL OF SPECIFIC COMPONENTS OTHER THAN CONTAINERS**

#### **A1 REFERENCES**

The following standards contain provisions that, through reference in this text, constitute provisions of this Annex. Where standards other than ISO standards are referenced they may be replaced by equivalent national standards.

##### **International Organisation for Standardization (ISO) Standards**

ISO 37: 1994	Rubber, vulcanised Or Thermoplastic - Determination Of Tensile Stress-strain Properties
ISO 188: 1998	Rubber, Vulcanised Or Thermoplastic - Accelerated Ageing And Heat Resistance Tests
ISO 1307: 1992	Rubber And Plastic Hoses For General purpose Industrial Applications - Bore Diameters And Tolerances, And Tolerances On Length
ISO 1402: 1994	Rubber And Plastic Hoses And Hose Assemblies - Hydrostatic Testing
ISO 1436: 1991	Rubber Hoses And Hose Assemblies - Wire Reinforced Hydraulic Type - Specification
ISO 4672: 1997	Rubber And Plastic Hoses - Sub-ambient Temperature Flexibility Tests
ISO 6957: 1988	Copper Alloys - Ammonia Test For Stress Corrosion Resistance
ISO 9227: 1990	Corrosion Tests In Artificial Atmospheres - Salt Spray Tests
ISO/DIS 11114-4: 2002	Transportable Gas Cylinders – Compatibility Of Cylinders And Valve Materials With Gas Contents – Part 4: Test Methods For Selecting Metallic Materials Resistant To Hydrogen Embrittlement
ISO/WD 17268: 2001	Gaseous Hydrogen – Land Vehicle Filling Connectors

##### **American Society for Testing and Materials (ASTM) Standards**

ASTM D572:	Test for Accelerated Aging of Vulcanised Rubber by Oxygen Pressure Method
------------	---

#### **A2 GENERAL REQUIREMENTS**

- A2.1 Unless otherwise stated in this Annex all tests shall be performed at 20°C ± 5°C.
- A2.2 Explosive gas mixtures shall be prevented from developing during the test procedures described in this Annex.
- A2.3 The test period for leakage and pressure tests shall be not less than 3 minutes.

A2.4 Unless otherwise stated the applied test pressure is to be measured at the inlet of the component under test.

### A3 APPROVAL REQUIREMENTS

#### A3.1 GENERAL APPROVAL REQUIREMENTS

A3.1.1 In addition to the requirements given below, the *Manufacturer* shall complete all documents referred to in **Part B** of this Annex and submit them to the Competent Authority when applying for type approval.

A3.1.2 The *Specific Components* shall be subjected to the applicable test procedures laid down in **Table 8A.1** of this Annex. The tests shall be conducted on *Specific Components* that are representative of normal production and complete with identification marks.

A3.1.3 The tests specified in Paragraphs **B3 to B8** of this Annex shall be conducted on the same samples of *Specific Components* in the sequence given in **Table 8A.1** unless otherwise indicated, e.g. for *Fittings* the Corrosion Resistance Test (**B3**) shall be followed by an Endurance Test (**B5**), followed by an External leakage Test (**B7**), and finally by a Hydrostatic Pressure Test (**B8**). If a *Specific Component* does not contain metallic sub-components the testing shall commence with the first applicable test.

A3.1.4 The documentation and test reports shall be sufficiently detailed that an independent third party test facility could reproduce the appropriate type approval tests and test results.

#### A3.2 SPECIFIC APPROVAL REQUIREMENTS

A3.2.1 Approval for a *Flexible Fuel Line* shall be given for one of any length with a minimum bending radius specified by the *Manufacturer* and when assembled with a specific type of *Fitting*.

A3.2.2 The construction of *Flexible Fuel Lines* shall be such that any reinforcing interlayer(s) are protected against corrosion by a cover. The cover shall prevent the formation of bubbles between the layer(s).

A3.2.3 The inside diameter of *Flexible Fuel Line* shall be in compliance with Table 1 of **ISO 1307**.

A3.2.4 *Flexible Fuel Lines* shall have an electrical resistance of less than 1 mega-ohm per meter.

A3.2.5 The profile of *Receptacles* shall comply with **ISO 17268**.

SPECIFIC COMPONENT	TYPE OF TEST						
	Material Tests <b>B1 &amp; B2</b>	Corrosion Resistance Test <b>B3</b>	Hydraulic Pressure Cycle Test <b>B4</b>	Endurance Test <b>B5</b>	Internal Leakage Test <b>B6</b>	External Leakage Test <b>B7</b>	Hydrostatic Pressure Test <b>B8</b>
Automatic Valves			—				—
Fittings			—				—
Flexible Fuel Lines			—				—
Heat Exchangers			—				—
Hydrogen Filters			—				—
Manual Valves			—				—
Non-Return Valves			—				—
Pressure Regulators			—				—
Pressure Relief Devices			—				—
Pressure Relief Valves			—				—
Receptacles			—				—
Sensors for Hydrogen Systems			—				—

**Table 8A.1:** Applicable Test Procedures For Specific Components Other Than Containers

## Annex 8: Part B

### APPROVAL TEST PROCEDURES FOR SPECIFIC COMPONENTS OTHER THAN CONTAINERS

#### MATERIAL TESTS

#### **B1 HYDROGEN COMPATIBILITY TEST**

##### B1.1 Sampling

The test applies to the materials used in a *Specific Component* where the material is in contact with hydrogen.

Number of material samples to be tested: 3

##### B1.2 Procedure and Requirements

- i) Aluminium alloys and steels complying with the material requirements of **ISO 7866** or **ISO 9809 - 1**.  
No additional tests are required if the materials comply with the requirements of **ISO 7866** or **ISO 9809 - 1**.
- ii) Other metallic materials  
Hydrogen compatibility shall be demonstrated in accordance with **ISO/DIS 11114 - 4**.
- iii) Non-metallic materials  
Hydrogen compatibility shall be demonstrated.

##### B1.3 Results

The results of the tests shall be presented in a test summary.

#### **B2 AGEING TEST**

##### B2.1 Sampling

All non-metallic materials used in a *Specific Component* shall be tested.  
Number of material samples to be tested: 3

##### B2.2 Procedure and Requirements

Special consideration shall be given to safety when conducting this test.

The test shall be undertaken in accordance with [REDACTED]. The sample shall be exposed to oxygen at the maximum material temperature in accordance with paragraph 2.4.5.1 of this regulation at 2 MPa for a period of 96 hours. Either the tensile strength and elongation or the microhardness shall comply with the specifications given by the *manufacturer*. No visible cracking of the test samples is allowed.

##### B2.3 Results

The results of the tests shall be presented in a test summary.

## **~~B2~~ — ~~AGEING TEST~~**

### ~~B2.1~~ — ~~Sampling~~

~~All non-metallic materials used in a *Specific Component* shall be tested.  
Number of material samples to be tested: 3~~

### ~~B2.2~~ — ~~Procedure and Requirements~~

~~Special consideration shall be given to safety when conducting this test.~~

~~The test shall be undertaken in accordance with **ASTM D572**. The sample shall be exposed to oxygen at 85°C at 2 MPa for a period of 96 hours. No cracking or visible evidence of deterioration of the test piece(s) is allowed.~~

### ~~B2.3~~ — ~~Results~~

~~The results of the tests shall be presented in a test summary.~~

## **BX Ozone COMPATIBILITY TEST**

### BX.1 Sampling

The test applies to elastomer materials

- where a sealing surface is exposed directly to air (e.g. facing seal of receptacle)
- used as a flexible fuel line cover.

Number of material samples to be tested: 3

### BX.2 Procedure and Requirements

The test shall be undertaken in accordance with .

The test samples shall be stressed to 20 percent elongation and exposed to air at 40°C with an ozone concentration of 0.5 parts per million for a period of 120 hours.

No visible cracking of the test samples is allowed.

### BX.3 Results

The results of the tests shall be presented in a test summary.

## **TESTS OF SPECIFIC COMPONENTS**

### **B3** **CORROSION RESISTANCE TEST**

#### B3.1 Sampling

Number of *Specific Components* to be tested: 3

#### B3.2 Procedure and Requirements

Test i) Metallic components shall be submitted to a 144 hour salt spray test in accordance with **ISO 9227** with all connections closed and shall meet the requirements therein.

Test ii) A copper alloy component shall also be submitted to 24 hours immersion in ammonia in accordance with **ISO 6957** with all connections closed and shall meet the requirements therein.

### B3.3 Results

The results of the tests shall be presented in a test summary.

## B4 HYDRAULIC PRESSURE CYCLE TEST

### B4.1 Sampling

~~This test applies to Pressure Relief Devices.~~

Number of *Specific Components* to be tested: 3

### B4.2 Procedure and Requirements

#### B 4.2.1 Pressure relief devices

*Pressure Relief Devices* shall be subjected to 1.5 times the number of *Filling Cycles* calculated in accordance with **Paragraph 2.4.6** of this Regulation at both the minimum and maximum material temperatures in accordance with **Paragraph 2.4.5** of this Regulation.

The pressure shall periodically change from 2 MPa to 1.25 times *NWorking Pressure* at a rate not exceeding 4 cycles per minute, except when tested at the minimum material temperature when the maximum test pressure shall be *NWorking Pressure*.

If fusible metal is used in a *Pressure Relief Device* it shall show no visible sign of extrusion.

#### B 4.2.2 Components other than pressure relief devices

The components shall be subjected to 3 times the number of *Filling Cycles* calculated in accordance with **Paragraph 2.4.6** of this Regulation.

The pressure shall periodically change from 2 MPa to 1.25 times *NWorking Pressure* at a rate not exceeding 4 cycles per minute.

Subsequently the *Component* shall fulfil the requirements of the Internal and External Leakage Tests (**B6 & B7**).

### B4.3 Results

The results of the tests shall be presented in a test summary.

## B5 ENDURANCE TEST

### B5.1 Sampling

Number of *Specific Components* to be tested: 3

### B5.2 Procedures And Requirements

#### B5.2.1 Automatic, Manual & Non-return Valves

The *Specific Component* shall be tested in accordance with the following procedure:

- i) Pressurise the *Specific Component* with dry air, nitrogen, or hydrogen to *NWorking Pressure* and subject it to 96% of the total number of test cycles in accordance with **Table B5.1** of this Annex at  $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ . A complete test cycle shall take place over a period of not less than  $10 \pm 2$  seconds. When in the closed position the downstream pressure of the component under test is allowed to decay to 0.5 times the *NWorking Pressure* of the component. The *Specific Component* shall fulfil the requirements of the Internal and External Leakage Tests (Paragraphs **B6 & 7** of this Annex respectively) at this temperature.
- ii) The *Specific Component* shall then be operated through 2% of the total number of test cycles at the minimum material temperature in accordance with **Paragraph 2.4.5.1** of this Regulation after 2 hours conditioning at this temperature. The *Specific Component* shall fulfil the requirements of the Internal and External Leakage Tests (Paragraphs **B6 & 7** of this Annex respectively) at this temperature.
- iii) The *Specific Component* shall then be operated through 2% of the total number of test cycles at the maximum material temperature in accordance with **Paragraph 2.4.5.1** of this Regulation after 2 hours conditioning at this temperature. The *Specific Component* shall fulfil the requirements of the Internal and External Leakage Tests (Paragraphs **B6 & 7** of this Annex respectively) at this temperature.

#### B5.2.2 Fittings

*Fittings* shall be subjected to 25 connection/disconnection cycles.

#### B5.2.3 Flexible Fuel Lines

Change new test to NWP

The length of the flexible part of the *Flexible Fuel Line* with its fittings attached, to be used in the following test shall be calculated as follows:

$$L = \pi R + 2D$$

where:

L = Length of the flexible part of the *Flexible Fuel Line*  
R = Minimum bending radius specified by the *Manufacturer*  
D = Outside diameter of the *Flexible Fuel Line*

The *Flexible Fuel Line* shall be bent through 180 degrees to the minimum radius specified by the *Manufacturer* and rigidly attached to a fixture in that position by the *Fittings* with which it is to be approved. One end of the *Flexible Fuel Line* shall be plugged and the other end shall be attached to a hydraulic

supply. The *Flexible Fuel Line* shall be pressurised quickly by means of a quick opening solenoid valve, such that one cycle consists of holding the pressure at 1.25 times the *Working Pressure* for  $10 \pm 1$  seconds (except for *Flexible Fuel Lines* with a required material temperature of  $120^{\circ}\text{C}$  where the hold pressure shall be 1.37 times *Working Pressure*) and then reducing it to less than 0.1 times the *Working Pressure* for  $5 \pm 0.5$  seconds. The total number of test cycles shall be equal to 2.0 times the number of *Filling Cycles* or *Duty Cycles* as appropriate to the use of the *Flexible Fuel Line* in accordance with Paragraph 2.4.6 or 2.4.7 of this Regulation as appropriate. 50% of the test cycles shall be performed at the minimum and the remaining 50% at the maximum material temperature in accordance with Paragraph 2.4.5.1 of this Regulation.

The *Flexible Fuel Line* shall not show any visible signs of damage.

#### B5.2.4 Pressure Regulators

Change to NWP

*Pressure Regulators* shall be tested in accordance with the following procedure:

- i) The *Pressure Regulator* shall be connected to a source of *Leak Test Gas* at *NWorking Pressure* and cycled through 95% of the number of *Duty Cycles* calculated in accordance with Paragraph 2.4.7 of this Regulation. One cycle shall consist of flow until stable outlet pressure has been attained, after which the gas flow shall be shutoff by a downstream quick closing valve until stable lockup pressure has been achieved. The *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (Paragraphs B6 & B7 of this Annex respectively) conducted at  $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$  at intervals of 20, 40, 60, 80 and 100% of the number of cycles required above.
- ii) The inlet of the *Pressure Regulator* shall be pressure cycled through 1% of the number of *Duty Cycles* from *NWorking Pressure* to 0.5 times the *NWorking Pressure* or less. Subsequently the *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (B6 & B7) conducted at  $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ .
- iii) The cycling procedure in i) above shall be repeated at the maximum material temperature in accordance with Paragraph 2.4.5.1 of this Regulation and at 1.25 times the *Working Pressure* for 1% of the number of *Duty Cycles*. Subsequently the *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (B6 & B7) conducted at the maximum material temperature.
- iv) The cycling procedure in ii) above shall be repeated at the maximum material temperature and at 1.25 times the working pressure for 1% of the number of *Duty Cycles*. Subsequently the *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (B6 & B7) conducted at the maximum material temperature.
- v) The cycling procedure in i) above shall be repeated at the minimum material temperature in accordance with Paragraph 2.4.5.1 of this Regulation and at *Working Pressure* for 1% of the number of *Duty Cycles*. Subsequently the *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (B6 & B7) conducted at the minimum material temperature.
- vi) The cycling procedure in ii) above shall be repeated at the minimum material temperature and at *Working Pressure* for 1% of the number of *Duty Cycles*. Subsequently the *Pressure Regulator* shall fulfil the requirements of the Internal and External Leakage Tests (B6 & B7) conducted at the minimum material temperature.

#### B5.2.5 Pressure Relief Devices

i) Creep Test

*Pressure Relief Devices* shall be hydrostatically pressurised to 1.25 times *NWorking Pressure* and held for 500 hours at a temperature ( $T_L$ ) calculated from the following equation:

$$T_L = T (0.057)^{(0.34 \log(T/T_f))}$$

where

$T_L$  = Test temperature, °C

$T_f$  = Activation temperature of the *Pressure Relief Device*, °C

$T$  = 82°C

Log is base 10

*Pressure Relief Devices* shall not show signs of creep and shall fulfil the requirements of the Internal Leakage Test (**Paragraph B6** of this Regulation) after being subjected to the above test.

ii) Activation Temperature

Following the Creep Test in i) above, the *Pressure Relief Devices* shall be pressurised with dry air, nitrogen, or hydrogen to *NWorking Pressure*. Subsequently the *Pressure Relief Devices* shall be exposed to an increasing temperature cycle starting from ambient temperature with a rate not exceeding 10 °C per minute until the specified activation temperature minus 10 °C is reached and then with a rate of not exceeding 2 °C per minute until the *Pressure Relief Devices* activate. The activation temperature shall correspond to the melting temperature of the fusible metal specified by the *Manufacturer* within a range of  $\pm 2$  °C. After activation the *Pressure Relief Devices* shall show no evidence of fragmentation.

#### B5.2.6 Pressure Relief Valves

Pressurise the *Pressure Relief Valve* for 25 cycles. A test cycle consists of pressurising the *Pressure Relief Valve* to the activation pressure causing the *Pressure Relief Valve* to open and vent. Once the *Pressure Relief Valve* is venting the inlet pressure shall be reduced causing the *Pressure Relief Valve* to re-seat. The cycle time shall be a period of  $10 \pm 2$  s. For the final cycle the activation pressure shall be reported and shall correspond to the activation pressure specified by the *Manufacturer* within a range of  $\pm 5\%$ . Activation pressures shall be at least **1.30 times** the *Working Pressure*.

#### B5.2.7 Receptacles

*Receptacles* shall be submitted to a number of connection/disconnection cycles equal to three times the number of *Filling Cycles* calculated in accordance with **Paragraph 2.4.6** of this Regulation. For each cycle the *Receptacle* shall be pressurised to 1.25 times the *NWorking Pressure*. Before depressurising, the nozzle shall be rotated by  $90^\circ$ .

#### B5.2.8 Sensors For Hydrogen Systems

If a sensor is intended to be installed into a *Hydrogen Component* and is subjected to the same number of *Duty Cycles* or *Filling Cycles*, it shall be

subjected to the same endurance test as the *Hydrogen Component* into which it is installed.

SPECIFIC COMPONENT	NO. OF TEST CYCLES
<i>Automatic Valve</i>	1.5 times the number of <i>Duty Cycles</i> or <i>Filling Cycles</i> in accordance with Paragraph 2.4.6 or 2.4.7 of this Regulation, as appropriate to the use of the valve.
<i>Manual Valve</i>	50
<i>Non-return Valve</i>	2.0 times the number of <i>Duty Cycles</i> or <i>Filling Cycles</i> in accordance with Paragraph 2.4.6 or 2.4.7 of this Regulation, as appropriate to the use of the valve.

Table B5.1: Test Cycles For Valves

### B5.3 Results

The results of the test shall be presented in a test summary.

## B6 INTERNAL LEAKAGE TEST

Change to NWP

### B6.1 Sampling

Number of *Specific Components* to be tested: 3

### B6.2 Procedure

The *Specific Components* shall be tested using *Leak Test Gas* and shall be pressurised at the inlet of the component when it is in its characteristic closed position and with the corresponding outlet port open.

The *Specific Component* shall be tested at the following conditions:

- i) At 20°C ± 5°C and at 0.02 times *Working Pressure* and at *Working Pressure*. Where an External Leakage Test (Paragraph B7 of this Annex) is also required at this temperature it may be undertaken before the next stage of this test.
- ii) At the minimum material temperature in accordance with Paragraph 2.4.5.1 of this Regulation, after 2 hours conditioning at this temperature and at 0.02 times *Working Pressure* and at *Working Pressure*. Where an External Leakage Test (Paragraph B7 of this Annex) is also required at this temperature it may be undertaken before the next stage of this test.
- iii) At the maximum material temperature in accordance with Paragraph 2.4.5.1 of this Regulation, after 2 hours conditioning at this temperature and at 0.02 times *Working Pressure* and 1.25 times *Working Pressure*, except for components with a required material temperature of 120°C where the higher test pressure shall be 1.37 times *Working Pressure*.

The component shall be observed for leakage with its outlet port open. The leakage can be determined by a flowmeter installed on the inlet side of the component or by another test method, which has been demonstrated to be equivalent.

### B6.3 Requirements

When pressurised the *Specific Component* shall stay bubble free for three minutes or shall not leak internally at a rate exceeding  $10 \text{ Ncm}^3$  per hour. The permitted leakage rate is applicable to tests with 100% hydrogen only. Permitted leakage rates for other gases or gas mixtures shall be converted to an equivalent leakage rate to that for 100% hydrogen.

### B6.4 Results

The results of the test shall be presented in a test summary.

## B7 EXTERNAL LEAKAGE TEST

Change to NWP

### B7.1 Sampling

Number of *Specific Components* to be tested: 3

### B7.2 Procedure

The *Specific Components* shall be tested using *Leak Test Gas* at the following conditions:

- i) At  $20^\circ\text{C} \pm 5^\circ\text{C}$  and at 0.02 times *Working Pressure* and at *Working Pressure*.
- ii) At the minimum required material temperature, in accordance with Paragraph 2.4.5.1 of this Regulation, after 2 hours conditioning at this temperature and at 0.02 times *Working Pressure* and at *Working Pressure*.
- iii) At the maximum required material temperature, in accordance with Paragraph 2.4.5.1 of this Regulation, after 2 hours conditioning at this temperature and at 0.02 times *Working Pressure* and 1.25 times *Working Pressure*, except for components with a required material temperature of  $120^\circ\text{C}$  where the higher test pressure shall be 1.37 times *Working Pressure*.

For heat exchangers this test shall only be undertaken on the hydrogen circuit.

### B7.3 Requirements

Throughout the test the *Specific Component* shall be free from leakage through stem or body seals or other joints, and shall not show evidence of porosity in casting, demonstrated by a surface active agent without formation of bubbles for 3 minutes or measured with a combined leakage and permeation rate less than  $10 \text{ Ncm}^3$  per hour (for *Flexible Fuel Lines* only  $10 \text{ Ncm}^3$  per hour per meter) or it shall be tested by using a demonstrated equivalent test method. The permitted leakage rate is applicable to tests with 100% hydrogen only. Permitted leakage rates for other gases or gas mixtures shall be converted to an equivalent leakage rate to that for 100% hydrogen.

### B7.4 Results

The results of the test shall be presented in a test summary.

## **B8 — HYDROSTATIC PRESSURE TEST**

### **B8.1 — Sampling**

~~Number of Specific Components to be tested: 3~~

### **B8.2 — Procedure And Requirements**

~~For a Specific Component upstream of and including the 1<sup>st</sup> PR The Component shall be pressurised to 2.0 times NWorking Pressure for a period of 10 minutes with the outlets plugged.~~

~~For a Specific Component downstream of the 1<sup>st</sup> PR The Component shall be pressurised to 1.3 times MAWP for a period of 10 minutes with the outlets plugged.~~

~~The Specific Component shall not leak nor show any visible evidence of permanent distortion and shall remain functional.~~

### **B8.3 — Results**

~~The results of the test shall be presented in a test summary.~~